



### MATERIAL SAFETY DATA SHEET

# SPARKO 33X-0182-0 PU TOPCOAT

SURFACE COATINGS

SURFACE COATINGS

#### Section 1. Chemical Identification

Product Name : SPARKO 33X-0182-0 PU TOPCOAT

Product Code : 33X-0182-0 (x denotes gloss level)

Dangerous Goods Class : 3

Packaging Type : In Kilograms (Kg)

Use : For wood and metal coating

SPARKO

SURFACE COATINGS

# Section 2. Components

#### **Chemical Identity**

Alkyd Resin

Toluene

Xylene

n-BAC

SCACACE COATINGS

Methyl Iso-Butyl Ketone

# Content

45%

8%

3/0

26%

10%

5%

570

6%

#### **CAS Number**

-

108 - 88 - 3

1330 - 20 - 7

123 - 86 - 4

111 - 15 E 9 CE COATINGS

108 - 10 - 1

# Section 3. Hazards Identification

**Swallowing** : Harmful if swallowed

Skin Absorption

SURFACE COATINGS

May cause irritation to skin. May cause

sensitization by skin contact.

SURFACE COATINGS

**Inhalation**: Trace component and residual monomer vapors

may be irritating to the eyes, mucous

membrane, respiratory tract, and may produce symptoms of headache and/or nausea in poorly

ventilated areas.

LUZON

REGIONAL OFFICE TAGUIG

1st Ave., Sta. maria Industrial Subd., Bagumbayan, Taguig City Tel #: (02) 506.8519; 837.0710 Fax #: (02) 519.1552 VISAYAS

HEADQUARTERS CEBU

ZEF SEA Olympus Building, AC Cortes Ave., Mandaue City, 6014, Cebu Clty Tel #: (032) 421.7817; 421.7262; 421.7863 Fax#: (032) 346.1817; 421.7877 MINDANAO

REGIONAL OFFICE DAVAO



Eye Contact : Direct contact may cause eye irritation.

SURFACE COATINGS

# Section 4. First-Aid Measures

SURFACE COATINGS

SURFACE COATINGS

**Eye Contact** 

Thorough flushing with water for at least 15

minutes. Get immediate medical assistance.

Skin Contact : Wash areas of contact repeatedly with soap and

water. Seek immediate medical assistance if

irritation persists. INGS

Ingestion : NEVER INDUCE VOMITING. Seek immediate

medical assistance.

Inhalation : Prevent further exposure. Seek immediate

medical assistance if dizziness, nausea or

unconsciousness is experienced.

### Section 5. Fire-Fighting Measures

Fire Extinguishing : CO<sub>2</sub>, foam, Dry powder. In case of larger fires,

water spray should be used.

In case of fire, formation of carbon monoxide, nitrogen oxide and traces of hydrogen cyanide is possible.

SURFACE COATINGS

SURFACE COATINGS

SURFACE COATING

Special fire fighting

equipment : Self-contained breathing apparatus should be

used by Fire fighters. Do not let contaminated extinguishing water into the soil, groundwater or

surface waters.

#### Section 6. Accidental Release Measure

Small spills can be washed off with large amounts of water; spills of a larger scale must be <u>PROPERLY DISPOSED</u>. The product may be toxic to aquatic lives; DO NOT dispose in natural bodies of water. Proper protective equipment should be worn. Do not empty into drains.



LUZON

۷۱

REGIONAL OFFICE TAGUIG

1st Ave., Sta. maria Industrial Subd., Bagumbayan, Taguig City Tel #: (02) 506.8519; 837.0710 Fax #: (02) 519.1552 VISAYAS

HEADQUARTERS

**CEBU**2F SEA Olympus Building, AC Cortes Ave.,
Mandaue City, 6014, Cebu Clty
Tel #: (032) 421.7817; 421.7262; 421.7863
Fax#: (032) 346.1817; 421.7877

MINDANAO

REGIONAL OFFICE DAVAO



Put on protective equipment. Remove sources of fire, ensure adequate ventilation/ exhaust ventilation. Keep unauthorized persons away.

Remove mechanically, cover remainders with wet, absorbent material (e.g. Sawdust, chemical binder based on calcium silicate hydrate, sand). After approx. one hour transfer to waste container. Keep damp in a safe ventilated area for several days.

# Section 7. Handling and Storage

Handling Ensure adequate ventilation or exhaust

> ventilation in the working area. Exhaust ventilation necessary if product is sprayed.

Avoid contact with skin and eyes.

Provide adequate ventilation and if necessary,

air extraction in working area. Explosion

protection required.

Keep container dry and tightly closed in cool and Storage

> well ventilated place. GS Keep away from flame.

UR = 50 ppm to 75 ppm

#### Section 8. Exposure Controls

SURFACE COATINGS

**N-Butyl Acetate** 

150 ppm to 200 ppm CAS No: 123-86-4 (8 hours average value)

maximum limit of excess factor 4

Methyl iso-Butyl Ketone

CAS No: 108-10-1 (8 hours average value)

maximum limit of excess factor

Toluene 100 ppm to 125 ppm CAS No: 108-88-3 (8 hours average value)

maximum limit of excess factor

maximum limit of excess factor

100 ppm to 125 ppm (8 hours average value)

LUZON

**Xylene** 

REGIONAL OFFICE **TAGUIG** 

1st Ave., Sta. maria Industrial Subd., Bagumbayan, Taguig City Tel #: (02) 506.8519; 837.0710 Fax #: (02) 519.1552

CAS No: 1330-20-7

VISAYAS

HEADQUARTERS CEBU

2F SEA Olympus Building, AC Cortes Ave., Mandaue City, 6014, Cebu Clty Tel #: (032) 421.7817; 421.7262; 421.7863 Fax#: (032) 346.1817; 421.7877

MINDANAO

REGIONAL OFFICE DAVAO

Unit A16 J. King Warehouse Complex Km. 3 Maa Road, Davao City 8000 Tel # (082) 244.1206 Fax #: (082) 285.2886

SURFACE COATINGS

SURFACE COATINGS





# Personal Protection

Respiratory protection SURFACE COATINGS

Respiratory protection required in insufficiently ventilated working areas and during spraying. CE COATINGS

An air-fed mask, or for short periods of work, a combination of charcoal filter and particulate

filter is recommend.

SURFACE COATINGS

Hand protection Conditionally suitable materials for protective

> gloves. Only suitable for brief exposure. In the event of contamination, change protective

gloves immediately.

SURFACE COATINGS

Wear eye/ face protection. **Eyes protection** 

**Body protection** Wear suitable protection clothing.

SURFACE COATINGS

#### Protection and hygienic measures

Keep away from foodstuffs, drinks and tobacco. Wash hands before breaks and at end of work. Keep working clothes separate. Take off immediately all contaminated clothing.

SURFACE COATINGS

SURFACE COATINGS

SURFACE COATINGS

SURFACE COATINGS

# Section 9. Physical and Chemical Properties

**Appearance** clear Color yellowish **Form** thick liquid smell of solvent Odor

Boiling point OATINGS 120 (248)Flash point 28 (82.4)

**Specific Gravity** 0.95 - 1.06

**Explosive limits** 1% (lower)

10.8% (upper)

Solubility in Water insoluble

LUZON

REGIONAL OFFICE **TAGUIG** 

1st Ave., Sta. maria Industrial Subd., Bagumbayan, Taguig City Tel #: (02) 506.8519; 837.0710 Fax #: (02) 519.1552

VISAYAS

HEADQUARTERS

CEBU

2F SEA Olympus Building, AC Cortes Ave., Mandaue City, 6014, Cebu Clty Tel #: (032) 421.7817; 421.7262; 421.7863 Fax#: (032) 346.1817; 421.7877

MINDANAO

(close cup)

REGIONAL OFFICE DAVAO

Unit A16 J. King Warehouse Complex Km. 3 Maa Road, Davao City 8000

Tel # (082) 244.1206 Fax #: (082) 285.2886



# Section 10. Stability and Reactivity

SURFACE COATINGS

Hazardous **Decomposition** 

Product No hazardous decomposition when stored and

handled correctly

exothermic reaction with amines and alcohols; **Hazardous Reaction** 

> reacts slowly with water forming CO2, in closed containers risk of bursting owing to increase of

pressure.

# Section 11. Toxicological information

**Acute toxicity** 

S LD50 oral, ratatings more than 5000 mg/kg Skin and mucous FACE COATINGS

membrane compatibility,

rabbit skin 4 hours exposure – very slight irritant.

very slight irritant Eyes

SURFACE COATINGS

# Section 12. Ecological information

Acute fish toxicity

6350 ppm/4H  $LC_{50}$ 

 $LD_{50}$ 5251 mg/Kg

# Section 13. Disposal Consideration URFACE

Do not allow to escape into waters, wastewater or soil.

The waste can be disposed of in a suitable incinerator under compliance with the relevant legislation.

SURFACE COATINGS

SURFACE COATINGS

After final product withdrawal, all residues must be removed from containers (drip-free, powder-free or paste -free). Once the product residues adhering to the walls of the containers have been rendered harmless, the product and hazard labels must be invalidated. Containers must be recycled in compliance with national legislation and environmental regulations.

SURFACE COATINGS

LUZON

REGIONAL OFFICE **TAGUIG** 

1st Ave., Sta. maria Industrial Subd., Bagumbayan, Taguig City Tel #: (02) 506.8519; 837.0710 Fax #: (02) 519.1552

VISAYAS

HEADQUARTERS CEBU

2F SEA Olympus Building, AC Cortes Ave., Mandaue City, 6014, Cebu Clty Tel #: (032) 421.7817; 421.7262; 421.7863 Fax#: (032) 346.1817; 421.7877

MINDANAO

REGIONAL OFFICE DAVAO





Incineration in compliance with local regulations.

# Section 14. Transport Information

SPARKO SURFACE COATINGS

**IMDG** : 3

IATA/ICAO
DOT 49 CFR
: 3
SURFACE COATINGS

# Section 15. Regulatory Information

Alkyd resin type paint

SPAR O

# Section 16. Others



The data and information contained in this Material Safety Data Sheet is provided to the best of our knowledge and ability on existing hazards, properties and handling of this product as recommended. It is recommended that the user tests the product according to its purpose. The user is responsible for the proper, safe and lawful use of this product. The information contained in this MSDS is subject to change without further notice. ©20

SURFACE COATINGS







#### LUZON

#### REGIONAL OFFICE TAGUIG

1st Ave., Sta. maria Industrial Subd., Bagumbayan, Taguig City Tel #: (02) 506.8519; 837.0710 Fax #: (02) 519.1552

#### VISAYAS

#### HEADQUARTERS CEBU

2F SEA Olympus Building, AC Cortes Ave., Mandaue City, 6014, Cebu Clty Tel #: (032) 421.7817; 421.7262; 421.7863 Fax#: (032) 346.1817; 421.7877

#### MINDANAO

#### REGIONAL OFFICE DAVAO



# PRODUCT SPECIFICATION SHEET

SURFACE COATINGS

# SPARKO 33X-0182-0 Polyurethane Topcoats

## CHEMICAL IDENTIFICATION

SURFACE COATINGS

SPARKO 33X-0182-0 Polyurethane Topcoat

Product Code : 33X-0182-0 (X denotes gloss level)

Available from 0 – 90 Sheen

PRODUCT FEATURES

**Product Description** 

It is a two-component clear Polyurethane topcoat with good alcohol and water resistance properties. It has excellent scratch, moisture and heat resistance. It comes in different gloss levels.

# SUITABLE WOOD-BASED SUBSTRATES

Floorings, Staircase, Bedroom Furniture, Billiard Tables, Bookshelves, Interior Doors, Dining and Kitchen Chairs, Dining Tables, Wall Units, Interior Wall Panels. Can also be applied to MDF, Bamboo and Metal.

### CHARACTERISTICS

Gloss Level COATINGS : 0 – 90 Sheen

Colour Availability : Clear and Pigmented

Scratch & Mar Resistance : High

Water & Alcohol Resistance : High

Sag Resistance : 127 µm

#### TECHNICAL SPECIFICATIONS

Solid Content (by weight) :  $52\% \pm 1\%$ Density (@, 25°C) : 1.04 Kg/L

Mixing Ratio O ATINGS : 2:1(310-0182-0 Hardener): 2(604 Thinner) O ATINGS

Pot Life : 4 Hours

Maximum Wet Film Thickness Theoretical Spreading Rate :  $127 \mu m$ :  $4-5 m^2/L$ 

SURFACE COATINGS

LUZON

REGIONAL OFFICE TAGUIG

1st Ave., Sta. maria Industrial Subd., Bagumbayan, Taguig City Tel #: (02) 506.8519; 837.0710 Fax #: (02) 519.1552 VISAYAS

HEADQUARTERS CEBU

ZEF SEA Olympus Building, AC Cortes Ave., Mandaue City, 6014, Cebu City Tel #: (032) 421.7817; 421.7262; 421.7863 Fax#: (032) 346.1817; 421.7877 MINDANAO

REGIONAL OFFICE DAVAO

Unit A16 J. King Warehouse Complex Km. 3 Maa Road, Davao City 8000 Tel # (082) 244.1206 Fax #: (082) 285.2886

SURFACE COATINGS



\*Approximate Drying Time: (@ 28°C, 74% humidity)

Dust Free = 45 - 60 min; Print Free = 45 - 60 min; Stacking = 24 hr

\*The drying time varies depending on film thickness, thinning and the environment.

Shelf Life  $@ 30^{\circ}C$  : 12 months

Packaging Sizes : 1 Kg, 4 Kg, 18 Kg

# SPARKO

SURFACE COATINGS

# HEALTH AND SAFETY

Proper personal protective equipment must be worn while using this product. This product should also be used in a well-ventilated spray booth. Avoid breathing in or smelling this product at all times. Please refer to our Material Safety Data Sheets (MSDS) for more health and safety details.

SURFACE COATINGS

The information contained in this product specification sheet has been provided based on our laboratory results. The type, quality and characteristics of substrates used, the environment of the end-user, individual systems or processes employed by the end-user and other conditions are elements which are beyond our control and we therefore recommend that the end-user test the product for the specific application, substrate required under the en-users environment and other working conditions. Sparko will not be held liable for damages to the improper use of our products. All information stated above are subject to change without prior notice. ©20

SURFACE COATINGS













#### LUZON

#### REGIONAL OFFICE TAGUIG

1st Ave., Sta. maria Industrial Subd., Bagumbayan, Taguig City Tel #: (02) 506.8519; 837.0710 Fax #: (02) 519.1552

#### VISAYAS

#### HEADQUARTERS CEBU

2F SEA Olympus Building, AC Cortes Ave., Mandaue City, 6014, Cebu Clty Tel #: (032) 421.7817; 421.7262; 421.7863 Fax#: (032) 346.1817; 421.7877

#### MINDANAO

#### REGIONAL OFFICE DAVAO